RHEOLUBE 374A



Rust Inhibited, Copper Deactivator

A lithium soap thickened, medium viscosity synthetic hydrocarbon grease designed for high speed and temperature applications.

MIL-PRF-32014A

	Lubricant Properties		Typical Value	Test Method
Recommended Service Range (°C)			-54 to 177	
Thickener			Lithium Soap	
Base Oil	Туре		Polyalphaolefin	
	Kinematic Viscosity	40°C	121 cSt	
		100°C	16.9 cSt	
	Viscosity Index		159	ASTM D-2270
	Flash Point	°C	276	ASTM D-92
	Typical Properties of	the	Typical Value	Test Method
	Grease			
Color, Appearance			Tan, Smooth	
Penetration	NLGI Grade		2	ASTM D-217
(1/10 mm)	Unworked		244	ASTM D-217
	Worked	60X	267	ASTM D-217
Density		25°C	0.86 g/cm ³	ASTM D-1480
Oil Separation	24 hour(s)	100°C	3.3	ASTM D-6184
Evaporation	24 hour(s)	100°C	0.29	

The typical properties shown on this product data sheet should not be used as a basis for preparing specifications. Refer to our product SDS for detailed safety information on this product.

(1904)