


# Lubenotes:

**Design Engineer's Guide to Selecting a Lubricant** 

## Greases for Rolling Element Bearings

Quality rolling element bearing greases function over a wide temperature range; offer thermooxidative stability and low volatility; and have base oils that retain the viscosity needed to provide an adequate lubricant film throughout a specified range of operating temperatures, speeds and loads. Using these general characteristics as the yardstick for selecting a lubricant will help ensure high performance and long life for rolling element bearing applications.



**Ultrafiltration services.** Nye will ultrafilter any of its oils and greases, and recommends this service for precision bearing applications to extend bearing life. Standards of cleanliness are clearly defined by the US Government for both oil and grease. MIL-STD-1246 includes five cleanliness levels for oil: 50, 25, 10, 5, and 1, where each number refers to the largest particle (in microns) allowed in an oil. There are three cleanliness levels for grease. Ultrafiltered grease can contain particles larger than 75 microns. Filtered or "clean grease" cannot have any particles larger than 75 microns, and there must be less than 1,000 particles per cubic centimeter between 24 and 74 microns in size (MIL-G-81322, Aircraft Grease). Ultrafiltered or "ultraclean grease" must not have any particles larger than 35 microns, nor may it have more than 1,000 particles per cubic centimeter between 10 and 34 microns in size (MIL-G-81937, Ultraclean Instrument Grease). Nye offers ultrafiltration services in a Class 100 environment for our own oils and greases – and for those of other manufacturers, which continues to be a sizable portion of our operations.

**Selecting the right lubricant for your application.** On the back is a partial list of Nye lubricants for rolling element bearings. Additional oils and greases are available to meet a wide range of application requirements. For technical specifications, evaluation samples, questions about any Nye products, or to discuss a lubricant custom-designed for your application — call us at +1.508.996.6721 or visit our website at NyeLubricants.com.



## **Greases for Rolling Element Bearings**

Grease (Temp. Range °C)	Oil	Thickener	NLGI Grade	Dropping Point (°C)	Evaporation	Water Washout	4-Ball Wear Scar	Rust Test	Application Notes
Rheolube® 374B (-40 to 150)	PAO	Lithium Soap	2	260	0.8%	4.1% (40°C)	0.45mm	pass	High load, lower-speed bearings
Rheolube® 374C (-40 to 150)	PAO	Lithium Soap	4	304	0.2%	2.8% (40°C)	0.66mm	pass	Light load, high-speed bearings
Rheolube® 374A (-54 to 177)	PAO	Lithium Soap	2	273	0.3%	3.2% (40°C)	0.44mm	pass	High-speed bearings, MIL-PRF-32014A
Rheoplex <sup>™</sup> 6000HT (-40 to 150)	Alkylated Naphtalene	Sodium Soap	2	>260	0.3%	8% (40°C)	0.44mm	pass	High speed bearings
Rheolube® 716R (-54 to 150)	Ester	Lithium Soap	2	185	0.2%	4.5% (40°C)	0.49mm	pass	Low-torque, precision bearings.
Rheotemp <sup>™</sup> 500 (-54 to 175)	Ester	Sodium Soap	2	212	0.64%	7.3%	0.48mm	-	High speed bearings.
Rheolube® 2000 (-45 to 125)	MAC	Sodium Soap	2	>260	0.1%	-	0.38mm	-	Aerospace and other low vapor pressure applications. Vapor pressure at 25°C = 10°8 torr
<u>Uniflor™ 8771</u> (-50 to 250)	PFPE	PTFE	2	Non- melting	0%	0.4%	0.56mm (20kg)	-	Wide-temperature bearings in extreme environments. Vapor pressure at 25°C = 10°9 torr
<u>Uniflor™8931</u> (-70 to 250)	PFPE	PTFE	2	Non- melting	0.13%	-	0.91mm	-	Wide temperature, low torque bearings in extreme environments. Vapor pressure at 25°C = 10°9 torr

### **Nye Product Test Protocols**

**Dropping Point** ASTM D-2265

**Evaporation** NYE CTM-1 (24 hrs. at 100°C) **Water Washout** ASTM D-1264 (60 min. at 80°C)

**4-Ball Wear Scar** ASTM D-2266 (1 hr., 75°C, 40 kg, 1200 RPM)

Rust Test ASTM D-1743

### Nye Lubricants, Inc. 12 Howland Road Fairhaven, MA 02719 USA Ph: +1.508.996.6721 NyeLubricants.com

Because we cannot anticipate or control the many different conditions under which this information and our products may be used, we cannot guarantee the applicability of this information or the suitability of our products in any individual situation. For the same reason, the products discussed are sold without warranty, expressed or implied. Statements concerning the possible use of our products are not intended as recommendations to use our product in the infrigement of any patent.

11-16